

MARYLAND METRICS

P.O.Box 261 Owings Mills, MD 21117 USA

(410)358-3130 (800)638-1830 Faxes: (410)358-3142 (800)872-9329
<http://mdmetric.com> techinfo@mdmetric.com

TECHNICAL INFORMATION and DATA

Mechanical properties for fine thread nuts according DIN-ISO

ISO 898/part 6

Nominal size (thread diameter)		Property class									
		04		05			5		6		
		Stress under proof load	Vickers hardness	Stress under proof load	Vickers hardness	Stress under proof load	Vickers hardness	Stress under proof load	Vickers hardness		
mm											
over	to	Sp N/mm ²	min. max.	Sp N/mm ²	min. max.	Sp N/mm ²	min. max.	Sp N/mm ²	min. max.	Sp N/mm ²	min. max.
7	10	380	188 302	500	272 353	690	175	302	770	188	302
10	16					720	190		780		
16	33								870		
33	39								920		

Nominal size (thread diameter)		Property class									
		8			10			12			
		Stress under proof load	Vickers hardness		Stress under proof load	Vickers hardness		Stress under proof load	Vickers hardness		
mm											
over	to	Sp N/mm ²	min. max.	Sp N/mm ²	min. max.	Sp N/mm ²	min. max.	Sp N/mm ²	min. max.		
7	10	955 ¹⁾ 890 ²⁾	250 ¹⁾ 195 ²⁾	353 ¹⁾ 302 ²⁾	1100 ¹⁾	1055 ²⁾	295 ¹⁾ 250 ²⁾	353	1200	295	353
10	16				1110 ¹⁾						
16	33	1030 ¹⁾	295 ¹⁾	353 ¹⁾	1080 ²⁾	260 ²⁾	353	-	-	-	
33	39	1090 ¹⁾									

¹⁾ Nuts style 1 (ISO 8673/DIN 971 part 1) < 0,8 d nuts

²⁾ Nuts style 2 (ISO 8674/DIN 971 part 2) < 1,0 d nuts

Failure loads for nuts with nominal height of 0,5 D

The values of failure loads given for guidance in the following table apply to different bolt classes. Bolt stripping is the expected failure mode for lower strength bolts, while nut stripping can be expected for bolts of higher property classes.

Minimum failure loads for nuts in % of the screws proof load (for guidance only)

Property class of the nut	Property class of the bolt			
	6.8	8.8	10.9	12.9
04	85	65	45	40
05	100	85	60	50